



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

TECHNICAL DATA SHEET

Pigment Yellow 139

1. Product Name

Trade Name:H4RP

C.I.:Pigment Yellow 139

C.I.No.:56298

CAS Number: 36888-99-0

Molecular Formula: C₁₆H₉N₅O₆

Formula Weight: 367.30

Chemical Group: Isoindoline

2. Physical, Chemical and Resistance Properties

Appearance: Yellow Powder

Shade: Similar to Standard

Tinting Strength:100%

Bulk Density(lb/gal): (Density(lb/gal): 1.74)

Moisture: ≤1.5

Oil Absorption(ml/100g): 45-69

Fineness(120 Mesh): ≤5.0

PH Value: 8

Water Soluble Matter (%) ≤1.5

Electric Conductivity (us/cm) ≤500

Acid Resistance 5

Alkali Resistance 5

Water Resistance: 5

Oil Resistance: 5

Alcohol Resistance 5

Ester Resistance 5

Benzene Resistance 5

Ketone Resistance -

Soap Resistance -

Bleeding Resistance 5

Migration Resistance -

Heat Resistance (°C) 270



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

Light Fastness (8=excellent) 8

3. Application

Application: plastic.

Recommended Application: Printing, water-base coating, solvent-base coating, water-base ink, solvent-base ink, offset ink

4. Packing

Packed in 25kgs Bag with Pallet.